

2025年12月31日

Attached hereto is a marked-up version of the changes made to the specification and claims by the current amendment. The attached page is captioned **“Version with markings to show changes made”**.

Respectfully submitted,

By:

Morrison & Foerster LLP
2000 Pennsylvania Avenue, N.W.
Washington, D.C. 20006-1888
Telephone: (202) 887-6924
Facsimile: (202) 263-8396

silicone adhesive is preferably from 0.75 to 3, in particular approximately 1% by weight, expressed in terms of the total silicone glue mass.

Paragraph beginning on line 4 of page 3 has been amended as follows:

When producing the composite, it is sufficient if the silicone glue is applied to ~~only one~~ of the parts to be bonded. ~~Which of the two parts to which it is applied is not important.~~
Application of the glue can be made to either of the two parts. The silicone glue is in this case, e.g. spread or applied using a dispenser technique to the parts.

Paragraph beginning on line 5 of page 4 has been amended as follows:

~~This means that~~ Hence, the silicone glue must compensate, in the working temperature range, for length changes which - expressed in terms of the dimensions of the magnetic pieces - may be a few 100 μm . If the elasticity is insufficient, stresses occur in the glue bond so as to cause strength losses and premature failure of the bond. This has been confirmed by shear-strength studies on bonds, especially after exposure to heating cycles.

Paragraph beginning on line 13 of page 4 has been amended as follows:

The production of a composite design according to the invention will be explained ~~in~~
~~more detail~~ below.

Paragraph beginning on line 15 of page 4 has been amended as follows:

An adhesive bed of the addition-crosslinking, single-component, self-adhesive silicone glue Q 3-6611 is first produced on one of the two parts. To that end, the silicone glue is spread over the parts with a layer thickness of about 100-125 μm . Since the silicone glue is a self-adhesive silicone glue, i.e. one provided with an internal adhesive, preliminary priming of the joint surface is not necessary. After the usual degreasing of the substrate surface, e.g. using a solvent, the silicone glue can be spread directly over the part. The wetting performance can be improved further, if required, by adding fumed silica. Glass spheres having a diameter of about 100 - 125 μm are then scattered over the prepared silicone glue bed in an amount of approximately 1% by weight, expressed in terms of the total silicone glue mass. The second part is then joined onto this layer, a spaced joint with a size equal to the diameter of the glass spheres

being created. The final strength of the composite is reached by curing the silicone adhesive for about 2 hours at approximately 150°C.

On page 6, please replace "Patent Claims" with --WHAT IS CLAIMED IS--.

